



<b>Reference</b>	E86o
<b>Description</b>	Two-component high-solids epoxy primer and finish coat based on zinc phosphate.
<b>Recommended use</b>	<p>Thixotropic primer and finish coat to protect steel structures against corrosion in an aggressive environment.</p> <p>Good resistance against water, oils and light chemicals.</p> <p>Can be applied in high film thicknesses.</p> <p>APECOAT COATING HS E86o is used as a primer and finish coat in high-quality epoxy polyurethane systems, with good performance on substrates that are not that well prepared.</p> <p>NOTE: Epoxy paints that are exposed to weathering will chalk and can change colour.</p>
<b>Composition</b>	Epoxy-Special polyamide-Zinc phosphate
<b>Support</b>	Steel, hot-dip galvanisation after treatment with suitable primer
<b>Colour</b>	Various RAL colours

## TECHNICAL INFORMATION AT 20°C AND 60% RH

**Density** ± 1.60 kg/l

**Drying time** Drying time (80 µ dry)

Dust free	Tack free	Recoatable with epoxy coatings	Recoatable with polyurethane coatings
		Minimum	Minimum
1-2 hours	4 hours	6 hours	12 hours

**Mixing ration** By volume: 83/17

**Dry volume weight** ± 70%

**Theoretical coverage** For 100µ dry: 7.0 m<sup>2</sup>/litre

**VOC** <290 g/litre

The values in this technical data sheet are typical values and can differ from batch to batch.

## RECOMMENDED USE

Recommended thickness	Application method	Roller	Brush	Airless
	Dry (μ)	60-80	60-100	80-200
Thinner	Thinner 118	Roller	Brush	Airless
	%	0-3	0-3	0-5
Cleaner	Thinner 118			
Temperature substrate	+3°C above dew point			
Relative humidity and temperature	Maximum 85% RH Minimum +5°C			
Processing time	4 hours			

## SUBSTRATE

Preparation	<p><b>Steel</b></p> <p>Remove any grease and contaminants, grit blast to Sa 2.5 and remove dust from the substrate. Can also be applied on a suitable primer. On manually prepared substrates to St3, apply the first coat with a brush to obtain good penetration of the paint.</p> <p><b>Old, sound, well-adhering paints</b></p> <p>Remove contaminants, degrease and sand the surface. Remove any rust to St3. Always test compatibility of the old paint with the subsequent coat.</p>
Maximum dry temperature	100°C

## SAFETY DATE

Flash point °C	Between 21°C and 55°C
Packaging	20 liter (16.6 liter base and 3.4 liter hardener)

See MSDS for further information.

## SHELF LIFE

Shelf life	24 months in original and sealed containers in a dry, covered storage space – temperature between 5 and 35 °C.
------------	--

The information contained in this technical data sheet was obtained from sources, which are reliable to the best of our knowledge can in no case imply our liability. Please ensure that you have the latest version of the Technical data sheet.

Date: 03/01/2018  
Edition: E86o.01.EN